



ETP CQU/B 2750

grease for bearings in very high speed.

Oil base	synthetic oil
Thickening agent	Li – 12 hydroxy stearate complex
Texture	smoot
Colour	ivory/white
Dropping point ASTM D - 566	> 180 °C
Operating temperature	- 55 up to 130 °C
DN FACTOR (speed factor)	10/6
Viscosity synthetic oil at 40 °C ASTM D- 445	150-175 cSt
NLGI grade classification	2
Worked penetration ASTM D-217	
60 strokes	255-265
10.000 strokes	285-295

جهت دریافت اطلاعات تخصصی و مشاوره فنی کافی است با مدیران فروش ما در ارتباط باشید

Site: www.enacol.com

Phone: +2122352437

Instagram: @enacol_razavifard